

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.



^{THE}
**Patent
Office**



INVESTOR IN PEOPLE

RECD 15 FEB 2001

WIPO

PCT

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

EP01391

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

AmBrewer

Dated

15 NOV 2000

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference GB Case PC/W-21923/P1/AC 533

0001883.8

2. Patent application number
(The Patent Office will fill in this part)

28 JAN 2000

3. Full name, address and postcode of the
or of each applicant
(underline all surnames)

Ciba Specialty Chemicals Water Treatments Limited
Cleckheaton Road
Low Moor
Bradford
West Yorkshire
BD12 OJZ

7585391001

Patent ADP number (if you know it)

If the applicant is a corporate body, give
the country/state of its incorporation

England

4. Title of invention

Polymerisation Process

5. Name of your agent (If you have one)

"Address for service" in the United
Kingdom to which all correspondence
should be sent
(including the postcode)

CIBA SPECIALTY CHEMICALS WATER TREATMENTS LIMITED
PATENTS DEPARTMENT
CLECKHEATON ROAD
LOW MOOR
BRADFORD
WEST YORKSHIRE
BD12 OJZ

7585391002

Patents ADP number (if you know it)

6. If you are declaring priority from one
or more earlier patent applications,
give
the country and the date of filing of the
or of each of these earlier applications
and (if you know it) the or each
application number

Country Priority application number
(if you know it)

Date of filing
(day/month/year)

7. If this application is divided or
otherwise derived from an earlier UK
application, give the number and the
filing date of the earlier application

Number of earlier
application

Date of filing
(day/month/year)

8. Is a statement of inventorship and of
right to grant of a patent required in
support of this request? (Answer 'Yes' if:

Yes

a) any applicant named in part 3 is not an
inventor, or

b) there is an inventor who is not named as
an applicant, or

c) any named applicant is a corporate body.

(see note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form -

Description 12
Claim(s) 3
Abstract 1
Drawing(s) -

10. If you are also filing any of the following, state how many against each item.

Priority documents -

Translations of priority documents -

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

X None filed

Request for preliminary examination and search (Patents Form 9/77) 1

Request for substantive examination (Patents Form 10/77) -

Any other documents (please specify) -

11.

I/We request the grant of a patent on the basis of this application

Signature

Date

J W Peatfield 27/1/2000

12. Name and daytime telephone number of person to contact in the United Kingdom

Mr J W Peatfield 01274 417401

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Polymerisation Process

The present invention relates to a process for making water soluble or water swellable polymers, by polymerisation of water soluble ethylenically unsaturated monomer or monomer blend. In particular the invention relates to processes of making said polymers containing low concentrations of residual monomer.

Water soluble and water swellable polymers are used in numerous industrial applications, for instance, flocculants, coagulants, rheology modifiers, dispersants, superabsorbents and binders. Of particular importance are high molecular weight water soluble polymeric flocculants which may be used as retention or drainage aids in paper making or to flocculate sludges such as sewage sludge, waste waters, textile industry effluents red mud from the Bayer Alumina process and suspensions of coal tailings etc.

It is standard practice to prepare water soluble or water swellable polymers by polymerising water soluble monomers using a suitable initiator system. The polymers are usually provided either as a solid particulate product or as a reverse phase dispersion or emulsion. Typically particulate polymers are prepared

Introducing initiators into an aqueous solution of the monomers and polymerising to form a polymer gel which is then cut into smaller pieces, dried and then ground to the appropriate particle size. Alternatively the polymers are produced as beads by suspension polymerisation or as a water-in-oil emulsion or dispersion by water-in-oil emulsion polymerisation, for example according to a process defined by EP-A-150933, EP-A-102760 or EP-A-126528.

It is known to produce water soluble and water swellable polymers using a variety of initiator systems. For instance it is common practice to polymerise water soluble monomers using redox initiator couples, in which radicals are generated by admixing with the monomer a redox couple which is a reducing agent and an oxidising agent. It is also conventional practice to use either alone or in combination with other initiator systems a thermal initiator, which would include any suitable

initiator compound that releases radicals at an elevated temperature. Other initiator systems include photo and radiation induced initiator systems, which require exposure to radiation to release radicals thereby effecting polymerisation. Other initiator systems are well known and well documented in the literature.

Although water soluble and water soluble polymers can be prepared on using many of the commercially available initiator systems, it is often difficult to prepare on an industrial scale polymers which have the correct molecular weight in combination with other desired characteristics, such as solubility, degree of absorbency etc. Over the last ten to fifteen years it has also become increasingly important to provide polymers which have extremely low levels of residual free monomer. This is particularly the case for polymers based on acrylamide monomer.

There have been various proposals in the literature for reducing residual free monomer concentrations in polymers, especially polymers of acrylamide. For instance in US-A-4906732 and US-A-4996251 polyacrylamides are treated with an amidase enzyme which is active towards acrylamide. However, although it was possible to achieve very low levels of free acrylamide, the enzymes proposed in these patents cannot consistently especially at elevated temperatures.

WO-A-97 29136 describes an amidase enzyme which is particularly effective at high temperatures and thus can be applied to the hot polymer gel substantially immediately prior to the drying stage. However, although this enzyme has shown particular advantages over other known amidases, it is still nonetheless difficult to consistently achieve low residual levels of acrylamide on an industrial scale.

Therefore there exists a need to be able to conveniently and consistently provide water soluble or swellable polymers with no or extremely low levels of residual monomer, especially acrylamide monomer.

There also exists a need to achieve this in an industrial scale process and in particular in a process which does not require additional long residence stages in the production process.

According to the invention we provide a process of preparing water soluble or water swellable polymer comprising the steps,

(a) forming an aqueous mixture comprising,

(i) a water soluble ethylenically unsaturated monomer or blend of monomers and,

(ii) an ultra violet initiator,

(b) effecting polymerisation by subjecting the aqueous mixture formed in step (a) to polymerisation conditions to form a polymer of said monomer or monomer blend,

(c) subjecting the polymer formed in step (b) to ultra violet light radiation, characterised in that the polymerisation step (b) is conducted substantially in the absence of ultra violet radiation

The water soluble or water swellable polymer is prepared by polymerisation of a water soluble monomer or water soluble monomer blend. By water soluble we mean that the water soluble monomer or water soluble monomer blend has a solubility in water of at least 5g in 100 ml of water. The polymerisation step (b) may employ conventional polymerisation techniques, provided that these do not result in exposure to ultra violet light.

The polymerisation step (b) may be effected by subjecting the aqueous monomer solution to any conventional polymerisation conditions which do not involve exposure to ultra violet radiation. Desirably this may be achieved by the use of redox initiators and/or thermal initiators. Typically redox initiators include a reducing agent such as sodium sulphite, sulphur dioxide and an oxidising compound such as ammonium persulphate or a suitable peroxy compound, such as tertiary butyl hydroperoxide etc. Redox initiation may employ up to 10,000 ppm (based on weight of monomer) of each component of the redox couple. Preferably

though each component of the redox couple is often less than 1000 ppm, typically in the range 1 to 100 ppm, normally in the range 4 to 50 ppm. The ratio of reducing agent to oxidizing agent may be from 10:1 to 1:10, preferably in the range 5:1 to 1:5, more preferably 2:1 to 1:2, for instance around 1:1.

Polymerisation step (b) may also be effected by employing a thermal initiator alone or in combination with other initiator systems, for instance redox initiators. Thermal initiators would include any suitable initiator compound that releases radicals at an elevated temperature, for instance azo compounds, such as azobisisobutyronitrile (AZDN), 4,4'-azobis-(4-cyanovaleric acid) (ACVA). Typically thermal initiators are used in an amount of up to 10,000 ppm, based on weight of monomer. In most cases, however, thermal initiators are used in the range 100 to 5,000 ppm preferably 200 to 2,000 ppm, usually around 1,000 ppm.

The water soluble or water swellable polymer prepared according to the process of the present invention may be cationic, anionic, nonionic or amphoteric. It may be substantially linear or alternatively branched or cross-linked. Cross-linked or branched polymers are prepared by incorporating a branching or cross-linking agent into the monomer blend. The cross-linking or branching agent may be for instance a di- or multifunctional material that reacts with functional groups pendant on the polymer chain, for instance multivalent metal ions or amine compounds which can react with pendant carboxylic groups. Preferably, however, the cross-linking or branching agent will be a polyethylenically unsaturated compound, which becomes polymerised into two or more polymer chains. Typically such cross-linking agents include methylene-bis-acrylamide, tetra allyl ammonium chloride, tri-allyl amine and polyethylene glycol di acrylate. The polymers may be highly crosslinked and therefore water insoluble but water swellable. Alternatively the polymer may be water soluble and either substantially linear or slightly branched, for instance prepared using less than 10 ppm cross-linking/branching monomer.

The water soluble or water swellable polymer may be cationic, anionic, amphoteric or non-ionic. Anionic polymers may be formed from one or more ethylenically

unsaturated anionic monomers or a blend of one or more anionic monomers with ~~for instance a nonionic monomer, preferably acrylamide. The anionic monomers~~ include acrylic acid, methacrylic acid, maleic acid, crotonic acid, itaconic acid, vinylsulphonic acid, allyl sulphonic acid, 2-acrylamido-2-methylpropane sulphonic acid and salts thereof. A preferred anionic polymer is the copolymer of sodium acrylate with acrylamide.

Cationic polymers may be formed from one or more ethylenically unsaturated cationic monomers optionally with for instance a nonionic monomer, preferably acrylamide. The cationic monomers include dialkylamino alkyl (meth) acrylates, dialkylamino alkyl (meth) acrylamides, including acid addition and quaternary ammonium salts thereof, diallyl dimethyl ammonium chloride. Preferred cationic monomers include the methyl chloride quaternary ammonium salts of dimethylamino ethyl acrylate and dimethyl aminoethyl methacrylate.

Amphoteric polymers include at least one cationic monomer (for example as defined above) and at least one anionic monomer (for example as defined above) optionally with a nonionic monomer, especially acrylamide.

~~Non-ionic polymers include polymers of any suitable non-ionic monomers, for~~ instance, acrylamide, methacrylamide, N-vinylpyrrolidone and 2-hydroxyethyl acrylate. Preferred non-ionic polymers comprise acrylamide especially acrylamide homopolymers.

Preferable water soluble or water swellable polymers comprise acrylamide.

The polymer produced by the process of the present invention may be a relatively low molecular weight polymer, for instance polymerised to a molecular weight below 100,000, for instance 2,000 to 10,000. Preferably however, the polymers are relatively higher molecular weight, for instance at least 100,000, especially at least 500,000. Typically the polymer has a molecular weight in the range of above 1 million to 20 or 30 million or higher. In general these high molecular weight

polymers tend to exhibit high intrinsic viscosities (IV), for instance at least 3 dl/g (measured at various polymer concentrations using standard techniques in 1N NaCl at 25°C). Preferably the polymer has an IV of at least 4 dl/g often at least 7 or 8 dl/g, for instance at least 12 dl/g. In some cases it may be highly desirable for the polymer to have an IV as high as 20 or 30 dl/g or even higher. However especially preferred polymers have an IV in the range 8 to 18 dl/g.

Typically an aqueous solution of water soluble monomer may be polymerised by solution polymerisation to provide an aqueous gel or by reverse phase polymerisation in which an aqueous solution of monomer is suspended in a water immiscible liquid and polymerised to form polymeric beads or alternatively by emulsifying aqueous monomer into an organic liquid and then effecting emulsion polymerisation. Examples of reverse phase polymerisation are given in EP-A-150933, EP-A-102760 or EP-A-126528. Preferably the polymer is prepared by solution polymerisation.


The process of the present invention requires that an aqueous monomer mixture is first formed comprising (i) a water soluble ethylenically unsaturated monomer or blend of monomers and (ii) an ultra violet initiator. In addition the aqueous monomer mixture may also contain other components, for instance redox initiators or thermal initiators or other compounds that may assist with the polymerisation step (b). The aqueous monomer mixture may also comprise other ingredients, for instance chain transfer agents which may be required to regulate the chain length.

The ultra violet initiator (ii) comprised in the aqueous monomer mixture may be any suitable initiator that remains substantially inert during the polymerisation step (b). Therefore the ultra violet initiator would generally be unsuitable if it decomposed during this initial polymerisation step. Therefore it is desirable to choose an ultra violet initiator that is not temperature sensitive at a temperature reached during the initial polymerisation step.


Desirably the ultra violet initiator is distributed homogenously throughout the aqueous monomer mixture, in order that it is evenly distributed throughout the resulting polymer. Preferably the ultra violet initiator is soluble or dispersible in the aqueous monomer or monomer blend.

We have surprisingly found that effective polymers can be produced by the process of the present invention, wherein an aqueous monomer blend which also contains an ultra violet initiator is first subjected to polymerisation in the absence of ultra violet light in which the ultra violet initiator remains substantially inert and then subjecting the polymer to ultra violet radiation.

Preferably the ultra violet initiator is a compound of formula:




wherein R₁ and R₂ are each independently C₁₋₃ alkyl or together form a C₄₋₈ cycloaliphatic ring, R₃ is H, C₁₋₂ alkyl or -O(CH₂CH₂)_nOH and n is 1-20. An especially preferred ultra violet initiator is the compound defined by the formula,



known as 1-[4-(2-Hydroxyethoxy)-phenyl]-2-hydroxy-2-methyl-1-propane-1-one supplied as Irgacure ® 2959 photoinitiator by Ciba Specialty Chemicals.

Another especially preferred UV initiator is the compound of the formula,



known as 1-phenyl-2-hydroxy-2-methyl-1-propane-1-one supplied as Darocure® 1173 photoinitiator by Ciba Specialty Chemicals.

Desirably the ultra violet initiator is used in an amount up to 10,000 ppm by weight of monomer. However, for economic reasons it is usually preferred not to use more than about 5,000. Suitable results are often obtained when the ultra violet initiator is included in an amount in the range 50 to 3,000 ppm, more preferably 100 to 2,500 ppm, especially 500 to 2,000 ppm.

The process involves the step of subjecting the polymer formed in the polymerisation step (b) to ultra violet radiation. This may be done by passing the formed polymer under ultra violet lamps. For instance the polymer may be passed from the reactor vessel and then irradiated with a suitable dose of ultra violet light and then passed to a drying section. Alternatively the polymer may be exposed to ultra violet radiation in the reactor vessel. Preferably the polymer is subjected to the ultraviolet light in the drying section. Thus in this preferred form of the

invention ultra violet lamps are mounted such that the polymer is exposed to ultra violet light whilst inside the drying equipment. More preferably the drying equipment is a fluid bed dryer and the ultra violet lamps are mounted inside the dryer.


It has further surprisingly been found that a water soluble or water swellable polymer in which the amount of residual monomer is below 100 ppm is obtainable by the process of the present invention, including any of the more specific embodiments.

According to a further aspect of the invention we provide a method of reducing the residual monomer content in a water soluble or water swellable polymer by


subjecting the polymer to ultra violet irradiation in the presence of an ultra violet initiator. ~~The ultra violet initiator may be applied to the surface of the formed~~ polymer and allowed to coat the surface of the polymer particles and then subjecting the polymer to ultra violet radiation. In a preferred form of this aspect of the invention the ultra violet initiator is actually absorbed into the polymer and is then preferably distributed throughout the polymer before being subjected to irradiation by ultra violet light. Alternatively the water soluble or water swellable polymer may be formed containing the ultra violet initiator distributed throughout the polymer. This may be for instance as a result of carrying out a process in accordance with the first aspect of the invention.

Preferably the method of reducing residual monomer is applied to polymers of acrylamide and said acrylamide polymer contains residual acrylamide monomer. More preferably the polymer of acrylamide is a relatively high molecular weight polymer and has an intrinsic viscosity of at least 4 dl/g, often at least 7 or 8 dl/g, for instance at least 12 dl/g. In some cases it may be highly desirable for the polymer of acrylamide to have an IV as high as 20 or 30 dl/g or even higher. Especially preferred are polymers of acrylamides which have an IV in the range 8 to 18 dl/g.


The ultra violet initiator may be any suitable ultra violet initiator as given herein before. It is preferred that the ultra violet initiator is water soluble or at least water dispersible. Preferably the ultra violet initiator is a compound of formula,



wherein R_1 and R_2 are each independently C_{1-3} alkyl or together form a C_{4-8} cycloaliphatic ring, R_3 is H, C_{1-2} alkyl or $-\text{O}(\text{CH}_2\text{CH}_2)_n\text{OH}$ and n is 1-20. Most preferably the ultra violet initiator either a compound of formula,



or a compound of formula



The following examples illustrate the invention, but are not intended to in any way limit the scope of the invention.

Examples

Test 1

2 tonnes of aqueous monomer mixture was prepared comprising 90% by weight acrylamide and 10% by weight dimethylaminoethyl acrylate methyl chloride quaternary ammonium salt and having a total monomer concentration of about 30%. Nitrogen gas was passed through the aqueous medium in order to remove dissolved oxygen or other volatile reactive species. 4.5 ppm potassium bromate KBrO_3 and 9ppm sodium sulphite Na_2SO_3 was combined with the aqueous monomer and mixed thoroughly. Polymerisation was allowed to proceed for two hours and the resulting polymer was dried using a fluid bed dryer.

Test 2

This was repeated but subjecting the gel to ultra violet radiation for 20 minutes during the drying process using a UV flood system from Starna using an intensity of $2 \times 10^{-4} \mu\text{W}/\text{cm}^2/\text{nm}$. These tests were repeated using various amounts of 1-[4-(2-Hydroxyethoxy)-phenyl]-2-hydroxy-2-methyl-1-propane-1-one (Irgacure ® 2959) in the monomer mixture.

Tests 3 to 6

~~The solubility, solution viscosity and residual acrylamide monomer were assessed~~
and the results are shown in Table 1.

Table 1

Test	UV initiator (ppm)	UV irradiation (min)	1% solution viscosity (cP)*	Solubility	Residual Acrylamide (ppm)
1	0	0	188	Good	881
2	0	20	199	Good	452
3	500	0	194	Good	964
4	500	20	182	Fair/Good	57
5	2000	0	176	Fair/good	960
6	2000	20	166	Good	47

measured using a Brookfield RVT viscometer at 30°s

Examples 7 to 12

Examples 1 to 6 were repeated but using a an aqueous solution of acrylamide monomer. Viscosity and residual acrylamide concentrations are shown in Table 2.

Table 2

Test	UV initiator (ppm)	UV irradiation (min)	1% solution viscosity (cP)#	Residual Acrylamide (ppm)
1	0	0	28	532
2	0	20	24	412
3	500	0	26	552
4	500	20	24	38
5	2000	0	28	639
6	2000	20	24	32

measured using a Brookfield RVT viscometer at 250°s

Claims

1. ~~A process of preparing water soluble or water swellable polymer comprising~~
the steps,

(a) forming an aqueous mixture comprising,

(i) a water soluble ethylenically unsaturated monomer or blend of monomers and,

(ii) an ultra violet initiator,

(b) effecting polymerisation by subjecting the aqueous mixture formed in step (a) to polymerisation conditions to form a polymer of said monomer or monomer blend,

(c) subjecting the polymer formed in step (b) to ultra violet light radiation, characterised in that the polymerisation step (b) is conducted substantially in the absence of ultra violet radiation.

2. A process according to claim 1 in which the polymerisation step (b) is effected by suitable polymerisation initiators, selected from the group consisting of redox initiators and thermal initiators.


3. A process according to claim 1 or claim 2 in which the polymer is formed from acrylamide.

4. A process according to any of claims 1 to 3 in which the polymer has an intrinsic viscosity of at least 4 dl/g.

5. A process according to any of claims 1 to 4 in which the polymer formed by solution polymerisation.


6. A process according to any of claims 1 to 5 in which the ultra violet initiator is soluble or dispersible in the aqueous monomer or monomer blend.

7. A process according to any of claims 1 to 6 in which the ultra violet initiator is a compound of formula:




wherein R_1 and R_2 are each independently C_{1-3} alkyl or together form a C_{4-8} cycloaliphatic ring, R_3 is H, C_{1-2} alkyl or $-\text{O}(\text{CH}_2\text{CH}_2)_n\text{OH}$ and n is 1-20.

8. A process according to claim 7 in which the ultra violet initiator is a compound of formula:



9. A process according to claim 7 in which the ultra violet initiator is a compound of formula:




10. A water soluble or water swellable polymer obtainable by a process defined by any of claims 1 to 9, in which the amount of residual monomer is below 100 ppm.

11. A process according to any of claims 1 to 10 in which step (c) is conducted simultaneous with a drying stage.

12. A method of reducing the residual monomer content in a water soluble or water swellable polymer by subjecting the polymer to ultra violet irradiation in the presence of an ultra violet initiator.


13. A method according to claim 12 in which the polymer is a polymer of acrylamide of intrinsic viscosity above 4 dl/g.

14. A method according to claim 12 or claim 13 in which the ultra violet initiator is a compound of formula:




wherein R_1 and R_2 are each independently C_{1-3} alkyl or together form a C_{4-8} cycloaliphatic ring, R_3 is H, C_{1-2} alkyl or $-O(CH_2CH_2)_nOH$ and n is 1-20.

15. A method according to claim 13 in which the ultra violet initiator is a compound of formula:



16. A method according to claim 13 in which the ultra violet initiator is a compound of formula:



Abstract

A process of preparing water soluble or water swellable polymer comprising the steps,

(a) forming an aqueous mixture comprising,

(i) a water soluble ethylenically unsaturated monomer or blend of monomers and,

(ii) an ultra violet initiator,

(b) effecting polymerisation by subjecting the aqueous mixture formed in step (a) to polymerisation conditions to form a polymer of said monomer or monomer blend,

(c) subjecting the polymer formed in step (b) to ultra violet light radiation, characterised in that the polymerisation step (b) is conducted substantially in the absence of ultra violet radiation. The process is particularly suitable for making highly effective water soluble and water swellable polymers useful as flocculants, coagulants, rheology modifiers, dispersants, superabsorbents and binders etc.
